# INTERNATIONAL STANDARD



Second edition 2003-04-01

## Lubricants, industrial oils and related products (class L) — Classification —

Part 9: Family X (Greases)

Lubrifiants, huiles industrielles et produits connexes (classe L) — Classification —

Partie 9: Famille X (Graisses)



Reference number ISO 6743-9:2003(E)

© ISO 2003



### PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

#### © ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Printed in Switzerland



### **Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this part of ISO 6743 may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 6743-9 was prepared by Technical Committee ISO/TC 28, *Petroleum products and lubricants*, Subcommittee SC 4, *Classifications and specifications*.

This second edition cancels and replaces the first edition (ISO 6743-9:1987), which has been technically revised.

ISO 6743 consists of the following parts, under the general title *Lubricants, industrial oils and related products (class L)* — *Classification*:

- Part 1: Family A (Total loss systems)
- Part 2: Family F (Spindle bearings, bearings and associated clutches)
- Part 3: Family D (Compressors)
- Part 4: Family H (Hydraulic systems)
- Part 5: Family T (Turbines)
- Part 6: Family C (Gears)
- Part 7: Family M (Metalworking)
- Part 8: Family R (Temporary protection against corrosion)
- Part 9: Family X (Greases)
- Part 10: Family Y (Miscellaneous)
- Part 11: Family P (Pneumatic tools)
- Part 12: Family Q (Heat transfer fluids)
- Part 13: Family G (Slideways)
- Part 14: Family U (Heat treatment)
- Part 15: Family E (Internal combustion engine oils)
- Part 3A: Family D (Compressors)
- Part 3B: Family D (Gas and refrigeration compressors)
- Part 99: General

Annex A of this part of ISO 6743 is for information only.



### Lubricants, industrial oils and related products (class L) — Classification —

Part 9:

Family X (Greases)

### 1 Scope

This part of ISO 6743 establishes a detailed classification of family X (Greases) which belongs to class L (Lubricants, industrial oils and related products).

It should be read in conjunction with ISO 6743-99<sup>[1]</sup>.

This classification applies to categories of greases used for lubrication of equipment, components of machines, vehicles, etc.

The greases have been classified according to the operating conditions under which they are used, because the versatile nature of grease makes it impractical to classify them according to the end use. It will therefore be necessary to consult the supplier to be certain that the grease can be used in, for example, rolling bearings or pumped supply systems, and also concerning the compatibility of products.

In this classification, a grease cannot have more than one symbol. This symbol should correspond to the most severe conditions of temperature, water contamination and load in which the grease can be used.

NOTE This part of ISO 6743 does not pretend to cover the classification of greases intended for very special applications. It is up to the end-user and the supplier to negotiate the applicability of such greases, on the basis of relevant laboratory and/or field testing.

### 2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this part of ISO 6743. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this part of ISO 6743 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 2137:1985, Petroleum products — Lubricating grease and petrolatum — Determination of cone penetration

ISO 8681:1986, Petroleum products and lubricants — Method of classification — Definition of classes

### 3 Explanation of symbols used

- **3.1** The detailed classification of family X is based on the conditions of grease use.
- **3.2** In accordance with ISO 8681, the complete designation of the grease includes:
- the initials ISO;
- the letter L for the class "lubricants, industrial oils and related products";

© ISO 2003 – All rights reserved



- the category of the grease constituted by a group of five letters where each letter and the order in which it is written has a particular significance:
  - the letter X for the family grease,
  - the lower operating temperature (symbol 1),
  - the upper operating temperature (symbol 2),
  - the ability of the grease to provide satisfactory lubrication in water contamination conditions, and to provide the level of anti-rust protection (symbol 3),
  - the ability of the grease to lubricate in the presence of high loads (symbol 4);
- the NLGI consistency number<sup>1)</sup> of the grease corresponding to the measured penetration level according to ISO 2137.
- **3.3** In this classification system, products are designated in a uniform manner, each letter having a significance of its own. It is therefore imperative that the order of writing shown in Table 1 be used.

For instance, a grease for use under the following operating conditions:

- lower operating temperature: − 20 °C;
- upper operating temperature: + 160 °C;
- water contamination: environmental conditions water wash;
- anti-rust: none;
- extreme pressure (EP): yes;
- NLGI consistency number: 00;

will have the ISO designation: ISO-L-XBEGB 00.

### 4 Detailed classification

The detailed classification is as follows.

The grease characteristics are determined according to the specifications detailed in annex A. From the test results, the correct designation symbols can be determined.

The operating-temperature range of the grease is determined from Table 2 and comprises two symbols: the lowest operating temperature and the maximum continuous operating temperature.

The ability of the grease to provide satisfactory lubrication in conditions where water contamination is possible, and to provide the level of anti-rust protection is described in Table 3.

Table 4 describes the requirements for symbol 4, according to the ability of the grease to lubricate in the presence of high loads.

The NLGI consistency makes up the final digits in the designation system (see Table 5).

1) For the definition of the NLGI consistency number, see ISO 6743-99<sup>[1]</sup>.

NLGI: National Lubricating Grease Institute



The detailed classification of greases is shown in Table 6.

Table 1 — Order of letters for designation of greases

| ISO               | L                   | Х             | Symbol 1                          | Symbol 2                          | Symbol 3            | Symbol 4   | NLGI number |
|-------------------|---------------------|---------------|-----------------------------------|-----------------------------------|---------------------|--|-------------|
| ISO initials      | Class of lubricants | Family grease | Lower<br>operating<br>temperature | Upper<br>operating<br>temperature | Water contamination | Ability ro lubricate under high loads [Extreme pressure (EP) properties] | Consistency |
| Example (see 3.3) |                     |               |                                   |                                   |                     |  |             |
| ISO               | L                   | Х             | В                                 | E                                 | G                   | В  | 00          |

Table 2 — Operating-temperature range

| Symbo            | ol 1        | Symbol 2 Upper operating temperature |          |  |
|------------------|-------------|--------------------------------------|----------|--|
| Lower operating  | temperature |                                      |          |  |
| Temperature (°C) | Symbol 1    | Temperature (°C)                     | Symbol 2 |  |
| 0                | A           | 60                                   | A        |  |
| -20              | В           | 90                                   | В        |  |
| -30              | С           | 120                                  | С        |  |
| -40              | D           | 140                                  | D        |  |
| < -40            | E           | 160                                  | E        |  |
|                  |             | 180                                  | F        |  |
|                  |             | > 180                                | G        |  |

Table 3 — Level of water resistance and protection against corrosion

| Water contamination <sup>a</sup> | Anti-rust protection <sup>b</sup> | Symbol 3 |
|----------------------------------|-----------------------------------|----------|
| L                                | L                                 | A        |
| L                                | M                                 | В        |
| L                                | Н                                 | С        |
| M                                | L                                 | D        |
| M                                | M                                 | E        |
| M                                | Н                                 | F        |
| Н                                | L                                 | G        |
| Н                                | M                                 | Н        |
| Н                                | Н                                 | I        |

a L = dry; M = static; H = water wash.

Table 4 — Ability to lubricate under high loads

| Extreme pressure (EP) properties | Symbol 4 |  |
|----------------------------------|----------|--|
| No                               | A        |  |
| Yes                              | В        |  |

© ISO 2003 – All rights reserved

 $<sup>^{\</sup>circ}$  L = no protection; M = protect in the presence of water; H = protect in the presence of salt water.